FrontLine

FrontLine™ Powder-Free Nitrile Exam Gloves were developed to offer the following:

- Human skin pH 5.5 balanced coating for reduced risk of irritation and perspiration
- Advanced non-latex nitrile polymer offers superior stretch and comfort
- Fully textured surface for improved grip in all conditions
- UL certified NFPA 1999-2018 edition
- Exceeds Puncture Resistance of NFPA 1999-2018 edition
- Fentanyl Permeation Testing: FrontLine™ has zero breakthrough with Fentanyl Citrate 100mcg/2ml for 240 minutes (test limit) per ASTM D6978. This assures EMS, Law Enforcement, and Corrections maximum protection in the event of inadvertent contact with synthetic opiates. Test results on file.
- Our EaseOff[™] non-stick exterior surface prevents tapes including Duct Tape and even Veni-Gard[™] from sticking to the glove
- AQL of 0.65 exceeding industry standards
- ExactFit[™] glove formers for reduced hand fatigue & improved dexterity
- ISO 13485 certified by an accredited registrar.

Ordering information

| Size | Catalog no. | Packaging |
|----------|-------------|----------------|
| Small | FL9-1 | 100 gloves/box |
| Medium | FL9-2 | 100 gloves/box |
| Large | FL9-3 | 100 gloves/box |
| XLarge | FL9-4 | 100 gloves/box |
| XXLarge | FL9-5 | 90 gloves/box |
| XXXLarge | FL9-6 | 90 gloves/box |

| Size | Catalog no. | Packaging |
|----------|-------------|----------------|
| Small | FL12-1 | 100 gloves/box |
| Medium | FL12-2 | 100 gloves/box |
| Large | FL12-3 | 100 gloves/box |
| XLarge | FL12-4 | 100 gloves/box |
| XXLarge | FL12-5 | 90 gloves/box |
| XXXLarge | FL12-6 | 90 gloves/box |

All packaging - 10 boxes/case



| Specifications | ASTM D6319 | NFPA 2018 Ed | FrontL FL9 | ine™ FL12 |
|-------------------------|---------------|-----------------|---------------|--------------|
| Length (in) | 9.05" | n/a | 9.5" | 12" |
| Fingertip (mils) | 1.9mil | n/a | 6mil | 6mil |
| Palm (mils) | 1.9mil | n/a | 5mil | 5mil |
| Cuff (mils) | n/a | n/a | 4mil | 4mil |
| Tensile strength | | | | |
| Before aging (MPa) | 14 | 14 | 20 | 20 |
| After aging (MPa) | 14 | 14 | 18 | 18 |
| Elasticity / elongation | | | | |
| Before aging (%) | 500% | 500% | 600 | 600 |
| After aging (%) | 400% | 500% | 510% | 510% |
| Puncture resistance | n/a | 1.01 lbs | 1.9 lbs | 1.9 lbs |



